

PRODUCT OVERVIEW

A high-loading black masterbatch for consistent colouring of polypropylene moulding and extrusion applications.

Base / family	Masterbatches and Additives	Primary process	Dosing / compounding
Supply form	Pellets	Standard colour	Black

TYPICAL PROPERTIES

Property / condition	Test method	Typical value	Unit
Carbon-black content	TGA / gravimetric method	40	wt. %
Carrier polymer	FTIR	Polypropylene	
Density, 23°C	ISO 1183-1	1.19	g/cm ³
Melt flow rate, 230°C/2.16 kg	ISO 1133-1	5	g/10 min
Moisture / volatile content	ISO 15512	≤ 0.20	wt. %
Dispersion rating at recommended dosage	Microscopy	≤ 3	grade
Recommended addition	End-use trial	1.0-5.0	%

Unless otherwise stated, standard specimen preparation and conditioning apply. Typical values are representative and are not minimum specification limits.

APPLICATIONS • Injection-moulded PP • PP sheet and profiles • Compounds • Selected fibre and nonwoven applications	KEY BENEFITS • 40% carbon black • PP-compatible carrier • High colour strength
--	---

PROCESSING GUIDELINES

Preblend or gravimetrically dose into compatible polypropylene. Typical addition is 1.0-5.0%. Fine-filtration variants are available for fibre and nonwoven applications.

PACKAGING AND STORAGE 25 kg PE-lined bags on pallets. Store dry, below 40°C, away from sunlight and direct heat. Recommended shelf life: 12 months in unopened packaging.	REGULATORY DOCUMENTATION Current safety and grade-specific regulatory documentation is available through Technical Service for the intended application and market.
---	---

The information in this document is provided for material selection and processing guidance. Suitability for a specific design, process and end use should be confirmed by the user under actual service conditions.